



Characterization of a well performing and durable Ni:CGO-infiltrated anode for metal-supported SOFC

Nielsen, Jimmi; Klemensø, Trine; Graves, Christopher R.; Blennow Tullmar, Peter

Publication date:
2012

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):

Nielsen, J., Klemensø, T., Graves, C. R., & Blennow Tullmar, P. (2012). *Characterization of a well performing and durable Ni:CGO-infiltrated anode for metal-supported SOFC*. Poster session presented at 10th Spring Meeting of the International Society of Electrochemistry, Perth, Australia. <http://spring10.ise-online.org/>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

s2c-022

Characterization of a well performing and durable Ni:CGO-infiltrated anode for metal-supported SOFC

Jimmi Nielsen, Trine Klemensø, Christopher Graves, Peter Blennow
Fuel Cells and Solid State Chemistry Division, Risø National Laboratory for Sustainable Energy, Technical University of Denmark, DK-4000, Denmark.
 jini@risoe.dtu.dk

A novel anode for metal supported solid oxide fuel cells (SOFCs) based on infiltration of Ni:CGO nano-sized particles on a metal based backbone was recently demonstrated on single cell level to show excellent performance and durability [1]. A degradation rate of 0.9 % pr. 1000 hours during in total 3000 hours of 0.25A/cm² galvanostatic testing at 650 °C was shown. Furthermore, it was shown on button cells that if the cathode side consisted of a dense CGO barrier layer in combination with a LSC cathode, a performance with an area specific resistance (ASR) of 0.27 Ωcm² at 650 °C could be obtained. These performance and durability characteristics are very encouraging but despite several papers on metal supported SOFC with this type of infiltrated anode [1-3], the performance and the factors controlling the performance and durability is not yet well understood. Only some initial data on symmetrical cells with Ni:CGO infiltrated metal based cermet anode with respect to temperature and water dependency has been reported [2-3]. Fig. 1 shows a Scanning Electron Microscopy (SEM) image of the infiltrated Ni:CGO nano particles.




Figure 1 SEM image of fractured infiltrated anode.

In the present paper we report a more detailed impedance characterization of the metal based anode with Ni:CGO infiltration by e.g. studying the influence of Ni content and impedance development during initial startup. Secondly, the effect of start-up temperature on the performance of the Ni:CGO infiltrated anode is studied. Finally, all previous reports with this type of anode have been performed with very low fuel utilization (FU). In the context of metal supported SOFC it is inherently interesting to study the technological relevant situation of high FU, as the tolerance towards corrosion, and the impact of corrosion on performance and durability, is critical. Therefore, the impact of high steam content in the fuel and hence corrosion of the metal based backbone is studied and characterized.

References:

- [1] T. Klemensø, J. Nielsen, P. Blennow, Å. H. Persson, T. Stegk, B. H. Christensen, S. Sønderby, J. Power Sources, 196 (2011) 9459.
- [2] P. Blennow, J. Hjelm, T. Klemensø, Å. Persson, S. Ramousse, M. Mogensen, Fuel Cells, 11 (2011) 661.
- [3] P. Blennow, J. Hjelm, T. Klemensø, S. Ramousse, A. Kromp, A. Leonide, A. Weber, J. Power Sources, 196 (2011), 7117.